



# RUBBER SHEETS

PHYSICAL PROPERTIES AND TECHNICAL INFORMATION

CODE

1015

TRADE NAME

Economic abrasion resistant sheet

POLYMER:

SBR

Anti-abrasive

CHARACTERISTICS	UNITS OF MEASURE	SPECIFICATIONS	VALUES	TOLERANCE
HARDNESS (H):	Sh.A3	ASTM D 2240	65	± 5
TENSILE STRENGTH (CR)	MPa	ASTM D 412C	6	min.
ELONGATION AT BREAK (AR)	%	ASTM D 412C	300	min.
TEAR STRENGTH	N/mm (.)	ASTM D 624B	25	min.
ABRASION RESISTANCE	mm <sup>3</sup>	DIN 53516	400	max.
SPECIFIC GRAVITY	g/cm <sup>3</sup>	DIN 53479	1,40	± 0,03

<b>AGEING</b> In: Air For: 72 h At: 70 °C	Δ H	Sh.A3	ASTM D 573	6
	Δ CR	%		- 30
	Δ AR	%		- 40
	Δ V	%		
<b>AGEING</b> In: Water For: 72 h At: 50 °C	Δ H	Sh.A3	ASTM D 471	-8
	Δ CR	%		
	Δ AR	%		
	Δ V	%		+ 8

WORKING TEMPERATURES					
In Air	°C	ASTM D 573	min:	- 25	max: + 70
In Oil	°C	ASTM D 471	min:		max:
In Water	°C	ASTM D 471	min:		max: +80

MAIN CHARACTERISTICS					
Elasticity	Compression	Abrasion	Flame	Fuels	Ozone
GOOD	GOOD	GOOD	POOR	UNSUITABLE	POOR

This data sheet has been issued with the greatest care and it is the result of several proofs made in our laboratory, according to specific norms. We don't ensure that the same tests carried out in other laboratories at the same conditions can give the same results.