



**ZAKŁADY CHEMICZNE
SPÓŁDZIELNIA PRACY
W GOLENIOWIE
POLAND**

CARD OF TECHNICAL PARAMETERS

PRODUCT: RUBBER FLOOR COVERING METRO OIL-RESISTANT

PROPERTIES	QUANTITY/UNIT	TESTING METHODS
Hardness (H)	75±5°ShA	PN-EN ISO 868
Tensile strength (TS _b) min	4 MPa	PN-ISO 37:2007
Resistance to heat ageing in the air at temp. 70°C after 72 hrs (SC) ΔTS _b ΔH	±30 ±10	PN-ISO 188:2000
Fragility temperature (T _k)	-30°C	PN-ISO 812:1999
Density (ρ) max	1,56 Mg/m ³	PN-ISO 2781+AC1:1996
The maximum increase in volume after exposure to oil IRM 903 (ΔV), at temp. 23°C after 72 h	+10%	PN-ISO 1817:2001/Ap1:2002

Zakłady Chemiczne Spółdzielnia Pracy 72-100 Goleniów ul. I Brygady Legionów 1/3
e-mail: sprzedaz@gumagoleniow.pl
www.gumagoleniow.pl

Annex no. 7 to TCA 2/2016