

TEST REPORT

Report No. : MAN:HL:7480009689

DATE : 04th November, 2016



ZENITH INDUSTRIAL RUBBER PRODUCT PVT. LTD.
 PLOT NO-C-15,C-16, C-17 PHASE 1,MIDC, DOMBIVLI (EAST)
 MUMBAI-421203
 INDIA
CONTACT PERSON : MR. KASHAVLAL KOIRI

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

SAMPLE DESCRIPTION PL 55110B PULLEY LAGGING RUBBER SHEET WITH NEOPRENE BONDING LAYER
COLOUR BLUE
COUNTRY OF ORIGIN INDIA
SAMPLE RECEIVING DATE 26/10/2016
TEST PERFORMING DATE 27/10/2016 TO 04/10/2016

Test Requested : Please refer to the result summary.

Test Method & Results : Please refer to next page(s).

Result Summary :	Test Requested	Conclusion
	US FDA 21 CFR 177.2600 (Rubber Articles) – Determination of Amount of Extractives	PASS

Per Pro SGS India Pvt Ltd.

Subasini Saraswat
Asst. Manager

Email your Test Report Related Enquiries at Feedback.HLT@sgs.com



Test Results :

US FDA 21 CFR 177.2600 (Rubber Articles) – Determination of Amount of Extractives

Method : With reference to US FDA 21 CFR 177.2600.

For use in contact with aqueous food:

Extractants	Test Condition	Result (mg/inch ²)	Reporting Limit (mg/inch ²)	Permissible Limit (mg/inch ²)
Distilled Water	Reflux temperature for 7 hours	<0.1	0.1	20
	Succeeding 2 hours of extraction	<0.1	0.1	1
Comment	--	PASS	--	--

Sample Description : PL 55110B PULLEY LAGGING RUBBER SHEET WITH NEOPRENE BONDING LAYER.

For use in contact with fatty food:


Extractants	Test Condition	Result (mg/inch ²)	Reporting Limit (mg/inch ²)	Permissible Limit (mg/inch ²)
n-Hexane	Reflux temperature for 7 hours	<0.1	0.1	175
	Succeeding 2 hours of extraction	<0.1	0.1	4
Comment	--	PASS	--	--

Sample Description : PL 55110B PULLEY LAGGING RUBBER SHEET WITH NEOPRENE BONDING LAYER.

- Note :
1. mg/inch² = milligram per square inch
 2. Test Condition has been provided by client.
 3. Above Test has been subcontracted to SGS approved lab.



Sample as Received



***** End of Report*****